



Cal-Neva Supply Co. Inc.

Everything in Rubber

www.calnevasupply.com

Commercial Neoprene 40 Duro

Commercial Neoprene 50-80 Duro

Physical Properties

Style #10 Commercial Neoprene 40 Duro

ASTM D-2000 Type BC • Color; Black

Durometer Hardness ShoreA ± 5	Tensile	Elongation	Temperature	Wt. per Linear Ft. .36"	Finish	Specifications
40	800	350	-20°F to +170°F	1/8" - 2.5	Smooth	ASTM D-2000, SAE J200, 1BC 408, Mil R 3065, SC 408Z1

Style #10 Commercial Neoprene 50-80 Duro

ASTM D-2000 Type BC • Color; Black

Durometer Hardness ShoreA ± 5	Tensile	Elongation	Temperature	Wt. per Linear Ft. .36"	Finish	Specifications
50	800	300	-20°F to +170°F	1/8" - 2.6	Smooth	ASTM D-2000, SAE J200, 1BC 508, Mil R 3065, SC 508
60	900	300	-20°F to +170°F	1/8" - 2.7	Smooth	ASTM D-2000, SAE J200, 1BC 609, Mil R 3065, SC 609
70	1,000	200	-20°F to +170°F	1/8" - 2.7	Smooth	ASTM D-2000, SAE J200, 1BC 710, Mil R 3065, SC 710
80	1,000	100	-20°F to +170°F	1/8" - 2.9	Smooth	ASTM D-2000, SAE J200, 1BC 810, Mil R 3065, SC 810