



Cal-Neva Supply Co. Inc.

Everything in Rubber

www.calnevasupply.com

**Elastomeric
Bearing Pad
Meets AASHTO**

Style 71 Elastomeric Bearing Pad

Meets AASHTO - Table B (Neoprene)

Durometer Hardness ShoreA ± 5	Thickness Inches	Width Inches	Tensile	Elongation	Temperature	Wt. Per Lin. Foot 36"	Finish	Specifications
50	1/8" thru 1"	48	2250	400	-40°F to +170°F	1/2" - 15.8	Smooth	Hardness - ASTM D-2240 Tensile - ASTM D-412 Heat Resist - ASTM D-573 Ozone ASTM 1149 Low Temp - ASTM D-2137 Comp Set - ASTM D-395 Tear Resistance - ASTM D-624
60	1/8" thru 1"	48	2250	350	-40°F to +170°F	1/2" - 16.0	Smooth	
70	1/8" thru 1"	48	2250	300	-40°F to +170°F	1/2" - 16.2	Smooth	